

# Thermal Laminate Phenolic

Thermal Laminate Board is a thermal insulation and dry-lining solution combined into a single board, making the product versatile for installation in a variety of locations within a building.

## **USES**

Designed for new build and refurbishment projects requiring a thermal upgrade.

Locating the product on the internal side of the structure is more responsive to heating conditions resulting in the ambient internal temperature becoming comfortable quicker within colder months, in addition to reducing thermal bridging through the structure.

Suitable for a variety of locations including application against masonry wall substrates or to the underside of rafters within a room in a roof application.

The board may be installed directly against masonry substrates or, where necessary, a suitable support system may be required to install the board such as timber battens or a metal drylining solution.

Not suitable for continuous high-humidity environments.



## **FEATURES AND BENEFITS**

- Locating the product on the internal side of the structure is more responsive to heating conditions resulting in the ambient internal temperature becoming comfortable quicker within colder months, in addition to reducing thermal bridging through the structure
- Apply directly to masonry substrates, metal dry-lining systems or timber battens
- Attach to the underside of rafters within a room in a roof application

# PRODUCT INFORMATION

#### Material

Phenolic Foam & Standard Wallboard

### **Product Density**

Reaction to fire as tested Test Method EN 13501-1 Plasterboard: A2-s1,d0

Plasterboard: 648kg/m<sup>3</sup>

Phenolic: B-s1,d0

Thermal Conductivity (W/mK)

Plasterboard: 0.19 Phenolic: 0.021

## **APPLICATION INSTRUCTIONS**

For Installation Instructions please refer to the Speedline Thermal Laminate Installation Guide www.speedlinedrywall.co.uk.

Product Code	Total Thickness (mm)	Plasterboard Thickness (mm)	Insulation Thickness (mm)	Length (mm)	Width (mm)	Thermal Resistance (m²k/w)	Calculated Weight (kg)
10703505	52.5	12.5	40	2400	1200	1.805	28.8
10691951	62.5	12.5	50	2400	1200	2.447	30.1
10691952	72.5	12.5	60	2400	1200	2.923	31.4
10691953	82.5	12.5	70	2400	1200	3.399	32.7
10691954	92.5	12.5	80	2400	1200	3.875	34